



2015000586E



检测  
CNAS L0690

# TEST REPORT

No: WT2015B02N01048

Entrusted by

SHANDONG FANGXING BUILDING  
MATERIALS CO.,LTD.

Sample

PSP Plastic Coated Steel Panel

Name

Test Type

Entrustment test

National Research Center of Testing  
Techniques for Building Materials



WT2015B02N01048







2015000586E




# National Research Center of Testing Techniques for Building Materials

## Test Report

No: WT2015B02N01048

Page 1 of 2

Sample Name	PSP Plastic Coated Steel Panel	Test Type	Entrustment test
Entrusted by	SHANDONG FANGXING BUILDING MATERIALS CO.,LTD.	Brand	
Manufacturer	SHANDONG FANGXING BUILDING MATERIALS CO.,LTD.	Sample Description	good condition
Sample Received Date	August 19,2015	Quantity	300mm×300mm 10pcs
Production Date/ Batch No.	—	Model/Size	—
Test Standard	GB/T 3857 - 2005 Test method for chemical resistance of glass fiber reinforced thermosetting plastics		
Test Items	1、 Chemical reagent resistance( 20%H <sub>2</sub> SO <sub>4</sub> 、 15%HCl、 20%H <sub>3</sub> PO <sub>4</sub> 、 5%NaOH、 20%HF、 20%HNO <sub>3</sub> 、 ammonia water、 chlorine water )		
Conclusion	*See page 2.*  Date of issued: August 26, 2015 (Seal) 		
Remarks:	( Blank )		

Approved by:  Verified by:  Compiled by: 

Test Institution Address: The South Mansion of China Building Materials Academy, Guanzhuang, Chaoyang District, Beijing, China Telephone: +86-010-65728538 Post Code: 100024



# National Research Center of Testing Techniques for Building Materials Test Report

No: WT2015B02N01048

Page 2 of 2

No.	Test Item	Test Results	Test Standard	
1	Chemical reagent resistance (120h)	20% $H_2SO_4$	No crack, loss of light, corrosion, bubble and other defects.	GB/T 3857 - 2005
		15% $HCl$	No crack, loss of light, corrosion, bubble and other defects.	
		20% $H_3PO_4$	No crack, loss of light, corrosion, bubble and other defects.	
		5% $NaOH$	No crack, loss of light, corrosion, bubble and other defects.	
		20% $HF$	No crack, loss of light, corrosion, bubble and other defects.	
		20% $HNO_3$	No crack, loss of light, corrosion, bubble and other defects.	
		Ammonia water	No crack, loss of light, corrosion, bubble and other defects.	
		Chlorine water	No crack, loss of light, corrosion, bubble and other defects.	
<b>Remarks:</b> ( Blank )				

Test Institution Address: The South Mansion of China Building Materials Academy, Guanzhuang,  
Chaoyang District, Beijing, China      Telephone: +86-010-65728538      Post Code: 100024



# 说 明

## Notice

- 1、本报告无中心“检验专用章”和骑缝章无效。

*This test report is invalid without the seal.*

- 2、本报告无“编制、审核、批准”签字无效。

*This test report is invalid without the signatures of the related persons.*

- 3、本报告涂改、部分复印无效。

*This test report is invalid if erased, altered or copied partially.*

- 4、对本报告若有异议，应于收到报告之日起十五日内向本中心提出，逾期恕不受理。

*Any doubt should inform us within 15 days after receiving the test report.*

- 5、委托检验样品和委托信息由委托人提供，中心不对其真实性负责，委托检验结果仅对来样负责。

*The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.*

- 6、本报告采用防伪纸张，复印后应带有网格底纹，数据页背面的编号为随机编号，与报告内容无关。

*This test report is printed on anti-counterfeiting paper. Its copy should have grid shading. The numbers on the back of the data sheet are random numbers not related with the report.*

本中心联系方式：

地址 (Address)：北京市朝阳区管庄东里1号

*No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.*

邮编 (Post Code)：100024

电话 (Tel)：(86-10) 65728538 51167681 / 7983 / 7984

传真 (Fax)：(86-10) 65715991

报告真伪查询：Tel: (86-10) 51167679

Fax: (86-10) 65764684

网址 (Web)：http://www.cbmtc.com

www.chinabmnet.com

www.ctc.ac.cn

电子邮箱 (E-mail)：baogao@ctc.ac.cn

